

TEST REPORT: 7191169605-CHM17-DCB

Date: 04 SEP 2017

Tel: +65 68851335 Fax: +65 67784301

Client's Ref:

Email: Sihai.LI@tuv-sud-psb.sg



PSB Singapore

Note: This report is issued subject to the Testing and Certification Regulations of the TÜV SÜD Group and the General Terms and Conditions of Business of TÜV SÜD PSB Pte Ltd. In addition, this report is governed by the terms set out within this report.

Choose certainty.
Add value.

SUBJECT

Testing of Tin Content in TBT-free Paint

CLIENT

ANS Surface and Technology Pte Ltd
4 Penjuru Place #01-18
2.8 Penjuru Tech Hub
Singapore 608782

Attn: Mr John Tan

SAMPLE SUBMISSION DATE / TEST DATE

28 Aug 2017 / 29 Aug 2017

DESCRIPTION OF SAMPLE

One can of paint was received, details as below

Sample Label : Stabilis AF100/200/300 Brown / Light Brown
Batch No. : M78033
Quantity : 250 ml

METHOD OF TEST

Total Tin Content by Atomic Absorption Spectrometry (AAS) after sample treatment.



TÜV SÜD PSB

Laboratory:
TÜV SÜD PSB Pte. Ltd.
No.1 Science Park Drive
Singapore 118221

Phone : +65-6885 1333
Fax : +65-6776 8670
E-mail: enquiries@tuv-sud-psb.sg
www.tuv-sud-psb.sg
Co. Reg : 199002667R

Regional Head Office:
TÜV SÜD Asia Pacific Pte. Ltd.
1 Science Park Drive, #02-01
Singapore 118221

TUV®



RESULTS

Sample Reference	Tin (as Sn), mg/kg	IMO Requirement, mg/kg
Stabilis AF100/200/300 Brown / Light Brown	Less than 100	2,500 max

Remark

The sample described below was tested and found to comply with the requirement specified in MEPC 49/22/Add.1 for organotin content by the International Maritime Organisation (IMO).

DULIN CHRISTIAN BRYAN
CHEMIST

for DR LI SIHAI
AVP / SENIOR CHEMIST
COATINGS & INDUSTRIAL CHEMICALS
CHEMICAL & MATERIALS

TEST REPORT: 7191169605-CHM17-DCB

04 SEP 2017



PSB Singapore

Please note that this Report is issued under the following terms :

1. This report applies to the sample of the specific product/equipment given at the time of its testing/calibration. The results are not used to indicate or imply that they are applicable to other similar items. In addition, such results must not be used to indicate or imply that TÜV SÜD PSB approves, recommends or endorses the manufacturer, supplier or user of such product/equipment, or that TÜV SÜD PSB in any way "guarantees" the later performance of the product/equipment. Unless otherwise stated in this report, no tests were conducted to determine long term effects of using the specific product/equipment.
2. The sample/s mentioned in this report is/are submitted/supplied/manufactured by the Client. TÜV SÜD PSB therefore assumes no responsibility for the accuracy of information on the brand name, model number, origin of manufacture, consignment or any information supplied.
3. Nothing in this report shall be interpreted to mean that TÜV SÜD PSB has verified or ascertained any endorsement or marks from any other testing authority or bodies that may be found on that sample.
4. This report shall not be reproduced wholly or in parts and no reference shall be made by the Client to TÜV SÜD PSB or to the report or results furnished by TÜV SÜD PSB in any advertisements or sales promotion.
5. Unless otherwise stated, the tests were carried out in TÜV SÜD PSB Pte Ltd, No.1 Science-Park Drive Singapore 118221.

July 2011